


# Diamond and Diamondlike Carbon as Wear-Resistant, Self-Lubricating Coatings for Silicon Nitride

Kazuhisa Miyoshi  
*Lewis Research Center*  
*Cleveland, Ohio*

Prepared for the  
International Tribology Conference  
sponsored by the Japanese Society of Tribologists  
Yokohama, Japan, October 29—November 2, 1995



National Aeronautics and  
Space Administration







3 1176 01422 9232

## DIAMOND AND DIAMONDLIKE CARBON AS WEAR-RESISTANT, SELF-LUBRICATING COATINGS FOR SILICON NITRIDE

Kazuhisa MIYOSHI

National Aeronautics and Space Administration  
Lewis Research Center  
Cleveland, Ohio 44135

Recent work on the friction and wear properties of as-deposited fine-grain diamond, polished coarse-grain diamond, and as-deposited diamondlike carbon (DLC) films in humid air at a relative humidity of approximately 40 percent and in dry nitrogen is reviewed. Two types of chemical vapor deposition (CVD) processes are used to deposit diamond films on silicon nitride ( $\text{Si}_3\text{N}_4$ ) substrates: microwave-plasma and hot-filament. Ion beams are used to deposit DLC films on  $\text{Si}_3\text{N}_4$  substrates. The diamond and DLC films in sliding contact with hemispherical bare  $\text{Si}_3\text{N}_4$  pins have low steady-state coefficients of friction ( $< 0.2$ ) and low wear rates ( $< 10^{-7} \text{ mm}^3/\text{N}\cdot\text{m}$ ), and thus, can be used effectively as wear-resistant, self-lubricating coatings for  $\text{Si}_3\text{N}_4$  in the aforementioned two environments.

**Keywords:** Diamond film, DLC film, Tribology, Wear, Friction

### 1. INTRODUCTION

Structural ceramics such as  $\text{Si}_3\text{N}_4$  and silicon carbide (SiC) are frequently the materials of choice in engine components, tools, and wear parts, such as turbine rotors, cutting tools, dies, mechanical-face seals, and rolling-element bearings. However, structural ceramics lack inherently good friction and wear properties. Clearly, what is needed is a means to provide acceptable levels of friction and wear properties for structural ceramics. Presently, liquid lubrication or some type of surface modification (e.g., coatings or ion implantation) is employed.

Coefficients of friction for diamond, known to be one of the slipperiest materials, are similar to those of polytetrafluoroethylene in terrestrial environments (1). Natural diamond or high-pressure and high-temperature manufactured diamonds are available as three-dimensional products. However, the CVD diamond films and diamondlike carbon (DLC) films are available in a planar film or sheet and can be grown economically on ceramics such as  $\text{Si}_3\text{N}_4$ . Diamond and DLC films could offer tribologists and designers the combined properties of hard coatings and solid lubrication (2).

In this investigation, fine-grain diamond, coarse-grain diamond, and DLC were deposited on monolithic  $\text{Si}_3\text{N}_4$  flat substrates. Reciprocating sliding-friction experiments were conducted with smooth flat surfaces of the diamond and DLC films in contact with hemispherical bare monolithic  $\text{Si}_3\text{N}_4$  pins in humid air and in dry nitrogen. Comparative experiments for friction and wear were also conducted with bare surfaces of monolithic  $\text{Si}_3\text{N}_4$  flats and a monolithic diamond (110) type IIa flat in contact with bare  $\text{Si}_3\text{N}_4$  pins. Some earlier data and experimental details on this work and related research are given in references 3 to 9.

### 2. EXPERIMENT

#### 2.1 Diamond and Diamondlike Carbon (DLC) Films

The as-deposited fine-grain diamond films were produced by a microwave plasma-enhanced CVD technique and are described in detail in references 3 and 4. The polished coarse-grain diamond films were produced by a hot-filament CVD technique and subsequently processed by diamond-wheel polishing. The deposition technique is described in detail in reference 9. The as-deposited DLC films, which are highly dense and pinhole-free, were produced by direct ion beam deposition from a Kaufman ion source (6).

A variety of techniques were used to characterize the diamond and DLC films. Scanning and transmission electron microscopy were used to determine surface morphology and to measure grain sizes. Surface profilometry was used to measure the surface roughness. Raman spectroscopy and Fourier transform infrared spectroscopy were used to characterize diamond quality and structure, while x-ray photoelectron spectroscopy (XPS) was used to characterize surface chemistry. Rutherford backscattering spectroscopy identified any impurities in the films and determined carbon and impurity concentrations. Proton recoil detection measured the hydrogen concentration and x-ray diffraction was used to determine the crystal orientation of the diamond films.

The physical characteristics of the diamond and DLC films are listed in table I. The average surface roughness of the two kinds of diamond and DLC films was small and ranged from 5 to 37 nm root-mean-square. The relatively smooth surface of the as-deposited fine-grain diamond, the polished coarse-grain diamond, and the as-deposited DLC films was attributed to the fine-grain microstructure, the diamond-wheel polishing, and the amorphous phase, respectively.

#### 2.2 Friction and Wear Experiments

Reciprocating sliding friction experiments were conducted with the flats (i.e., diamond and DLC films, monolithic diamond (110) type IIa, and bare monolithic  $\text{Si}_3\text{N}_4$ ) in contact with the bare monolithic  $\text{Si}_3\text{N}_4$  pins in a humid air at a relative humidity of approximately 40 percent and in dry nitrogen. Details of the friction apparatus, the experimental procedures, and the wear measurements are described in reference 4; the experimental conditions are listed in table II. Hot-pressed, polycrystalline, magnesia-doped silicon nitride ( $92 \text{ Si}_3\text{N}_4\text{-}4\text{MgO-}4\text{Y}_2\text{O}_3$ ) was used as the flat and pin materials in the sliding friction experiments and as the substrate material for diamond and DLC films.

### 3. FRICTION AND WEAR PROPERTIES

Figure 1 presents coefficients of friction in humid air and dry nitrogen for the as-deposited fine-grain diamond film, the as-deposited DLC film, and the bare  $\text{Si}_3\text{N}_4$  flat in sliding contact with the bare  $\text{Si}_3\text{N}_4$  pins. The friction data indicate that the steady-state coefficient of friction was considerably lower for the as-deposited fine-grain diamond and as-deposited DLC films than for bare  $\text{Si}_3\text{N}_4$  flat in humid air and dry nitrogen. Using a smooth diamond and DLC film with a  $\text{Si}_3\text{N}_4$  substrate reduces the steady-state coefficient of friction to an acceptable level (e.g.,  $<0.2$ ) in humid air and dry nitrogen. Note that the frictional results on the as-deposited fine-grain diamond and DLC films couple are consistent with those on the natural monolithic diamond (111) in humid air and dry nitrogen (5).

Generally, for the diamond film, the coefficient of friction decreased with an increase in the number of passes regardless of environment, reaching an equilibrium value after a certain number of passes. The high initial coefficients of friction observed for the as-deposited fine-grain diamond film in humid air and dry nitrogen predominantly resulted from the plowing or microcutting actions of some sharp edges of asperities present on the as-deposited fine-grain diamond film surface. As the sliding continued and the pin passed repeatedly over the same track, the tips of the sharp edges of asperities on the track quickly became dull and the coefficient of friction was appreciably affected by blunting the edges of asperities. Therefore, the coefficient of friction is markedly reduced in the initial stage of the experiment.

For the DLC film, the coefficient of friction was almost constant in a humid-air environment, but decreased with the increasing number of passes in dry nitrogen, reaching an equilibrium value. For the bare  $\text{Si}_3\text{N}_4$  flat, the coefficient of friction increased with an increase in number of passes regardless of environment, reaching an equilibrium value after a certain number of passes. For the bare  $\text{Si}_3\text{N}_4$  flat, the low initial coefficients of friction observed in humid air and dry nitrogen predominantly resulted from a contaminant layer formed on  $\text{Si}_3\text{N}_4$  surfaces by the interaction of the surface with the environment.

Thin contaminant layers are unavoidably present on every surface of any solid that has been exposed to air or nitrogen. The layers are made up of contaminants such as adsorbed gases, water vapor, and hydrocarbons and have a thickness of atomic dimensions (around 2-nm thick). These contaminants can greatly reduce friction and accordingly provide lubrication as seen in the initial stage of the experiment. Under the repeated sliding, the contaminant surface layers are removed, thus, direct contact of the fresh surfaces is unavoidable. This situation applies to the sliding contact in the condition of steady-state (equilibrium) coefficient of friction for the  $\text{Si}_3\text{N}_4$ - $\text{Si}_3\text{N}_4$  couples (fig. 1b).

It is well known that sliding action in humid air increases the chemical reaction rate between  $\text{Si}_3\text{N}_4$  and water vapor. Many researchers have found that the tribochemical interactions produce reaction products (i.e., silicon dioxide) and lead to a decrease in the coefficient of friction for the  $\text{Si}_3\text{N}_4$ - $\text{Si}_3\text{N}_4$  couple (e.g., 10). The frictional results for the bare  $\text{Si}_3\text{N}_4$  flat shown in figure 1 are consistent with many researchers' findings. However, for the diamond and DLC films, the formation of silicon dioxide on the counterfacing  $\text{Si}_3\text{N}_4$  pin in humid air leads to increases in the coefficient of friction. The presence of the silicon oxide layer on the bare  $\text{Si}_3\text{N}_4$  pin plays a role in the relatively high friction process for the diamond and DLC films.

Figure 2 presents steady-state (equilibrium) coefficients of friction and wear rates in humid air and dry nitrogen for the as-deposited fine-grain diamond, polished coarse-grain diamond, and as-deposited DLC films, bare monolithic diamond (110) type IIa flat, and bare monolithic  $\text{Si}_3\text{N}_4$  flat in contact with bare  $\text{Si}_3\text{N}_4$  pins. The friction and wear data indicate conditions that reduce friction (e.g., a particular combination of environment and material) usually reduce wear rate as well.

The results presented in figure 2 demonstrate that the as-deposited fine-grain diamond, polished coarse-grain diamond, and DLC films improved both friction and wear properties of  $\text{Si}_3\text{N}_4$ . The steady-state coefficients of friction and the wear rates of the bare  $\text{Si}_3\text{N}_4$  flat are high in humid air and dry nitrogen. On the other hand, all the as-deposited fine-grain diamond, polished coarse-grain diamond, DLC, and diamond (110) type IIa flat in contact with bare  $\text{Si}_3\text{N}_4$  pins have a low steady-state coefficient of friction ( $<0.2$ ) and a low wear rate ( $10^{-7} \text{ mm}^3/\text{N}\cdot\text{m}$  or less). Those carbon films can be effective wear-resistant, self-lubricating films for ceramics.

### 4. CONCLUDING REMARKS

As-deposited fine-grain diamond, polished coarse-grain diamond, and as-deposited DLC films can be effectively used as wear-resistant, self-lubricating coatings for silicon nitride ( $\text{Si}_3\text{N}_4$ ) in humid air and dry nitrogen. Those films (deposited on  $\text{Si}_3\text{N}_4$  substrates) in sliding contact with bare  $\text{Si}_3\text{N}_4$  pins in humid air at a relative humidity of 40 percent and in dry nitrogen have low steady-state coefficients of friction ( $<0.2$ ) and low wear rates ( $<10^{-7} \text{ mm}^3/\text{N}\cdot\text{m}$ ).

### 5. ACKNOWLEDGMENTS

The author thanks R.L.C. Wu, A. Garscadden, and P.N. Barnes of the Wright Laboratory for depositing the microwave plasma CVD diamond films and for performing Rutherford backscattering spectroscopy, proton recoil detection, and x-ray diffraction; M. Murakawa, S. Takeuchi, and S. Miyake of the Nippon Institute of Technology for depositing the hot-filament CVD diamond films; and S. Heidger and D.T. Jayne for Raman and XPS analysis.

### 6. REFERENCES

- (1) Bowden, F.P. and Tabor, D., *The friction and lubrication of solids*, pt. 2, Clarendon Press (1964) 159-185.
- (2) Gigl, P.D., New synthesis techniques, properties and applications for industrial diamond, Presented at the *DA Ultrahard Materials Seminar* (1989).
- (3) Wu, R.L.C., et al., Synthesis and characterization of fine grain diamond films, *J. Appl. Phys.*, **72**, 1 (1992) 110-116.
- (4) Miyoshi, K., et al., Friction and wear of plasma-deposited diamond films, *J. Appl. Phys.*, **74**, 7 (1993) 4446-4454.
- (5) Miyoshi, K., Wu, R.L.C., and Garscadden, A., Friction and wear of diamond and diamondlike carbon coatings, *Surf. Coat Technology*, **54/55** (1992) 428-434.
- (6) Wu, R.L.C., Miyoshi, K., Vuppaladhadiam, and Jackson, E., Physical and tribological properties of rapid thermal annealed diamondlike carbon films, *Surf. Coat. Tech.*, **54/55** (1992) 576-580.
- (7) Miyoshi, K. Pouch, J.J., and Alterovitz, S.A., Plasma-deposited amorphous hydrogenated carbon films and their tribological properties, *Materials Science Forum*, **52, 53** (1989) 645-656.
- (8) Miyoshi, K., Friction and wear of plasma-deposited amorphous hydrogenated films on silicon nitride, *Adv. Info. Storage Syst.*, **3** (1991) 147-160.

- (9) Murakawa, M. and Takeuchi, S., Forming of a grinding wheel using a dresser with brazed diamond film, *Mat. Sci. Eng.*, A140 (1991) 759-763.

- (10) Fischer, T.E., Liang, H., and Mullins, W.M., Tribochemical lubricious oxides on silicon nitride, *Mat. Res. Soc. Symp. Proc.*, 140 (1989) 339-344.

TABLE I.—COMPARISON OF AS-DEPOSITED FINE-GRAIN DIAMOND, POLISHED COARSE-GRAIN DIAMOND, AND AS-DEPOSITED DIAMONDLIKE CARBON (DLC) FILMS

Condition	As-deposited fine-grain diamond film	Polished coarse-grain diamond film	As-deposited DLC film
Composition	Essentially carbon, < 2.5 at % hydrogen	Essentially carbon	70 at % carbon and 30 at % hydrogen
Microstructure	Polycrystalline	Polycrystalline	Amorphous
Crystal orientation	<110>	<111>	-----
Grain size, nm	20 to 100	10 000	-----
Raman spectrum	Sharp peak centered near 1330 cm <sup>-1</sup> ; broad humps centered near 1320 cm <sup>-1</sup> and in 1500 to 1530 cm <sup>-1</sup> range	Sharp peak centered near 1330 cm <sup>-1</sup> ; broad humps centered near 1320 cm <sup>-1</sup> and in 1500 to 1530 cm <sup>-1</sup> range	Broad peak at 1539 cm <sup>-1</sup> ; weak shoulder peak around 1340 cm <sup>-1</sup>
Atom-bonding state	sp <sup>3</sup> and sp <sup>2</sup> (variable ratio, very roughly 1:1)	sp <sup>3</sup> and sp <sup>2</sup> (variable ratio)	sp <sup>3</sup> and sp <sup>2</sup>
Surface morphology	Granulated or spherulitic: spherical asperities of different sizes	Flat, polished	Pinhole-free uniform smooth surface
Surface roughness, rms, nm	6 to 37	6 to 25	5
X-ray photoelectron spectroscopy (XPS) spectrum	Carbon and oxygen peaks	Carbon and oxygen	Carbon and oxygen
C/O ratios in XPS spectrum	8 to 12	10	-----

TABLE II.—CONDITIONS OF SLIDING FRICTION EXPERIMENTS IN HUMID AIR AND DRY NITROGEN

[Pin specimens were polished with 3- $\mu$ m diamond powder and 1- $\mu$ m aluminum oxide powder, respectively. Hemispherical pin specimen radius, 1.6 mm.]

Contact .....	Hemispherical pin on flat configuration
Load, N .....	1
Environment .....	Humid air (relative humidity 40 percent) and dry nitrogen (relative humidity less than 1 percent)
Temperature, °C .....	23
Motion .....	Unidirectional sliding
Sliding velocity, mm/min .....	86
Total passes .....	30 000




Figure 1.—Coefficients of friction for as-deposited fine-grain diamond film, as-deposited DLC film, and bare Si<sub>3</sub>N<sub>4</sub> flat in contact with Si<sub>3</sub>N<sub>4</sub> pins as function of number of passes. (a) Humid air. (b) Dry nitrogen.




Figure 2.—Coefficients of friction and wear rates of as-deposited fine-grain diamond, polished coarse-grain diamond, as-deposited DLC, diamond (110) type IIa, and Si<sub>3</sub>N<sub>4</sub> in contact with Si<sub>3</sub>N<sub>4</sub> in humid air and dry nitrogen.

1

2

3

4

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE September 1995	3. REPORT TYPE AND DATES COVERED Technical Memorandum		
4. TITLE AND SUBTITLE Diamond and Diamondlike Carbon as Wear-Resistant, Self-Lubricating Coatings for Silicon Nitride		5. FUNDING NUMBERS  WU-505-63-5A		
6. AUTHOR(S) Kazuhisa Miyoshi				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Lewis Research Center Cleveland, Ohio 44135-3191		8. PERFORMING ORGANIZATION REPORT NUMBER  E-9735		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, D.C. 20546-0001		10. SPONSORING/MONITORING AGENCY REPORT NUMBER  NASA TM-106974		
11. SUPPLEMENTARY NOTES Prepared for the International Tribology Conference sponsored by the Japanese Society of Tribologists, Yokohama, Japan, October 29—November 2, 1995. Responsible person, Kazuhisa Miyoshi, organization code 5140, (216) 433-6078.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT  Unclassified - Unlimited Subject Category 27  This publication is available from the NASA Center for Aerospace Information, (301) 621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Recent work on the friction and wear properties of as-deposited fine-grain diamond, polished coarse-grain diamond, and as-deposited diamondlike carbon (DLC) films in humid air at a relative humidity of approximately 40 percent and in dry nitrogen is reviewed. Two types of chemical vapor deposition (CVD) processes are used to deposit diamond films on silicon nitride (Si <sub>3</sub> N <sub>4</sub> ) substrates: microwave-plasma and hot-filament. Ion beams are used to deposit DLC films on Si <sub>3</sub> N <sub>4</sub> substrates. The diamond and DLC films in sliding contact with hemispherical bare Si <sub>3</sub> N <sub>4</sub> pins have low steady-state coefficients of friction (< 0.2) and low wear rates (< 10 <sup>-7</sup> mm <sup>3</sup> /N-m), and thus, can be used effectively as wear-resistant, self-lubricating coatings for Si <sub>3</sub> N <sub>4</sub> in the aforementioned two environments.				
14. SUBJECT TERMS Diamond film; DLC film; Tribology; Wear; Friction			15. NUMBER OF PAGES 6	
			16. PRICE CODE A02	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT	





National Aeronautics and  
Space Administration  
**Lewis Research Center**  
21000 Brookpark Rd.  
Cleveland, OH 44135-3191

Official Business  
Penalty for Private Use \$300

POSTMASTER: If Undeliverable — Do Not Return

